

## Further Exploration of Ultimate Limits of Flux Pinning in Nb<sub>3</sub>Sn

Lance D. Cooley

Applied Superconductivity Center, National High Magnetic Field Laboratory and Department of Mechanical Engineering, Florida State University; Tallahassee, Florida 32310, USA

E-mail: [ldcooley@asc.magnet.fsu.edu](mailto:ldcooley@asc.magnet.fsu.edu)

**Abstract** – Envisioned magnets for high-energy physics would demand unprecedented flux-pinning performance from Nb<sub>3</sub>Sn conductors. Accordingly, recent research has questioned whether the native pinning by the grain-boundary network in modern conductors, with ~100 nm grain size, is able to attain the needed performance. One set of experiments has augmented grain-boundary pinning with intragranular damage clusters created by irradiation, which has a side-effect of increasing electron scattering and the upper critical field. A second group of experiments has sought to reduce grain size to < 50 nm by addition of zirconia and rare-earth oxide nanoparticles, which could also function as point pins. In both cases, the shape of the bulk pinning-force curve is improved for high-field applications, where the peak of the curve shifts from 20% to >30% of the irreversibility field. Stimulated by these efforts, we envision two experiments using thin films of Nb<sub>3</sub>Sn, possibly obtained by deposition of Nb onto bronze, which could extend understanding further. Past work found that grain size could be varied from > 200 to < 20 nm for deposition at different temperatures, where the Nb<sub>3</sub>Sn forms in-situ. These changes lead to a shift of the pinning-force curve peak toward higher field like the effects seen in present-day experiments. Coupling these films with subsequent exposure to proton irradiation allows a systematic variation of each potential pinning center to understand the balance of grain-boundary vs cluster pinning. It also achieves pinning conditions at the extreme of both methods. In the second experiment, gradients in pinning-center distribution could be realized by forcing Nb-Sn reactions to occur along thermal gradients and by using the diverging portion of an irradiation beam. Among the interesting physics questions posed by a gradient configuration are whether asymmetric critical states can be formed, whether field-cooled configurations with non-zero macroscopic current exist, and what the arrangement of pinned flux lines becomes.

*Acknowledgements:*

The work done at Florida State University is supported by the U.S. Department of Energy, Office of Science, and Office of High Energy Physics under Award No. DE-SC0018379. A portion of this work was performed at the National High Magnetic Field Laboratory, supported by National Science Foundation Cooperative Agreement No. DMR-1644779 and the State of Florida.

**Keywords (Index Terms)** – Flux pinning, artificial pinning centers, niobium tin, niobium titanium, pinning mechanism.

IEEE-CSC & ESAS SUPERCONDUCTIVITY NEWS FORUM (global edition), No. 46, February 2019.

Received December 21, 2018; selected December 24, 2018. Reference STP625; Category 5.

This invited presentation 1MOr1B-02 was given at ASC 2018, October 28-November 02, 2018, Seattle (USA).